

## Einsatzempfehlung

Material	Stahl N/mm <sup>2</sup>		Rostfreie Stähle		Guss		NE-Metalle			Superleg.		Stahl gehärtet			
Zugfestigkeit	<500	<800	<1200 (<HRC38)	<1600 (<HRC48)	<800	<1200	GG	GGG	Al Knetleg.	Al Si<10%	Cu,Ms	Ti/Ni/Co <900	900-1500	HRC 48-57	HRC 58-63
40 00 867 678 - Vc (m/min)	12	10			4			6	20						
Kühlung	Emulsi- on/Öl	Emulsi- on/Öl			Emulsi- on/Öl		Emulsi- on/Öl		Emulsi- on/Öl						